





RAM
WINDOWS

**NEW CONSTRUCTION WINDOWS
THERMAL PERFORMANCE**

**SERIES 800
FIXED HEAVY PICTURE WINDOW**

PRODUCT SERIES	GLAZING TYPE	U-FACTOR	SHGC	VLT
Series 800 Fixed Heavy Picture Window	PPG SB 70XL Low-E I.G. w/ Argon Gas	0.34	0.25	0.57
	Cardinal 270 Low-E I.G. w/ Argon Gas	0.33	0.33	0.62
	Cardinal 340 Low-E I.G. w/ Argon Gas	0.33	0.16	0.35
	Cardinal 366 Low-E I.G. w/ Argon Gas	0.32	0.25	0.58
	PPG SB 70XL Low-E I.G. w/ Argon Gas & Muntins	0.34	0.22	0.52
	Cardinal 270 Low-E I.G. w/ Argon Gas & Muntins	0.33	0.30	0.56
	Cardinal 340 Low-E I.G. w/ Argon Gas & Muntins	0.33	0.15	0.31
	Cardinal 366 Low-E I.G. w/ Argon Gas & Muntins	0.32	0.22	0.52

Test Methods: NFRC 100-2004 for U-Factor, NFRC 200-2004 for SHGC and Visible Light Transmittance



For more information on RAM Windows, visit us online at www.ramwindows.com or call us at 281-495-9056.





RAM
WINDOWS

**NEW CONSTRUCTION WINDOWS
THERMAL PERFORMANCE**

**SERIES 840
FIXED HEAVY PICTURE WINDOW
(INSIDE GLAZED)**

PRODUCT SERIES	GLAZING TYPE	U-FACTOR	SHGC	VLТ
Series 840 Fixed Heavy Picture Window (Inside Glazed)	PPG SB 70XL Low-E I.G. w/ Argon Gas	0.36	0.25	0.57
	Cardinal 270 Low-E I.G. w/ Argon Gas	0.35	0.33	0.62
	Cardinal 340 Low-E I.G. w/ Argon Gas	0.35	0.17	0.35
	Cardinal 366 Low-E I.G. w/ Argon Gas	0.35	0.25	0.58
	PPG SB 70XL Low-E I.G. w/ Argon Gas & Muntins	0.36	0.23	0.51
	Cardinal 270 Low-E I.G. w/ Argon Gas & Muntins	0.35	0.30	0.56
	Cardinal 340 Low-E I.G. w/ Argon Gas & Muntins	0.35	0.16	0.31
	Cardinal 366 Low-E I.G. w/ Argon Gas & Muntins	0.35	0.23	0.52

Test Methods: NFRC 100-2004 for U-Factor, NFRC 200-2004 for SHGC and Visible Light Transmittance



For more information on RAM Windows, visit us online at www.ramwindows.com or call us at 281-495-9056.





RAM
WINDOWS

**NEW CONSTRUCTION WINDOWS
THERMAL PERFORMANCE**

**SERIES 900
CASEMENT WINDOW**

PRODUCT SERIES	GLAZING TYPE	U-FACTOR	SHGC	VLT
Series 900 Casement Window	PPG SB 70XL Low-E I.G. w/ Argon Gas	0.42	0.20	0.45
	Cardinal 270 Low-E I.G. w/ Argon Gas	0.41	0.27	0.49
	Cardinal 340 Low-E I.G. w/ Argon Gas	0.40	0.13	0.27
	Cardinal 366 Low-E I.G. w/ Argon Gas	0.40	0.20	0.45
	PPG SB 70XL Low-E I.G. w/ Argon Gas & Muntins	0.42	0.19	0.41
	Cardinal 270 Low-E I.G. w/ Argon Gas & Muntins	0.41	0.25	0.45
	Cardinal 340 Low-E I.G. w/ Argon Gas & Muntins	0.40	0.13	0.25
	Cardinal 366 Low-E I.G. w/ Argon Gas & Muntins	0.40	0.19	0.41

Test Methods: NFRC 100-2004 for U-Factor, NFRC 200-2004 for SHGC and Visible Light Transmittance



For more information on RAM Windows, visit us online at www.ramwindows.com or call us at 281-495-9056.





RAM
WINDOWS

**NEW CONSTRUCTION WINDOWS
THERMAL PERFORMANCE**

**SERIES 990
AWNING WINDOW**

PRODUCT SERIES	GLAZING TYPE	U-FACTOR	SHGC	VLТ
Series 990 Awning Window	PPG SB 70XL Low-E I.G. w/ Argon Gas	0.42	0.20	0.45
	Cardinal 270 Low-E I.G. w/ Argon Gas	0.40	0.26	0.48
	Cardinal 340 Low-E I.G. w/ Argon Gas	0.40	0.14	0.27
	Cardinal 366 Low-E I.G. w/ Argon Gas	0.40	0.20	0.45
	PPG SB 70XL Low-E I.G. w/ Argon Gas & Muntins	0.42	0.19	0.41
	Cardinal 270 Low-E I.G. w/ Argon Gas & Muntins	0.40	0.24	0.44
	Cardinal 340 Low-E I.G. w/ Argon Gas & Muntins	0.40	0.13	0.24
	Cardinal 366 Low-E I.G. w/ Argon Gas & Muntins	0.40	0.19	0.40

Test Methods: NFRC 100-2004 for U-Factor, NFRC 200-2004 for SHGC and Visible Light Transmittance



For more information on RAM Windows, visit us online at www.ramwindows.com or call us at 281-495-9056.